

TITANIUM ALLOY

TYPICAL APPLICATIONS

Tubing in aircraft and engine hydraulic systems
 Corrosion resistant pipes and vessels
 Recreational products – golf club shafts, tennis racquets, bicycle frame
 Foil in honey-comb

PRODUCT DESCRIPTION

Titanium Grade 9 is sometimes referred to as 'half 6-4'. This alloy of titanium with 3% aluminium and 2.5% vanadium offers 20 to 50% greater mechanical strength than the commercially pure (CP) titanium grades, but is more formable and weldable than Ti-6Al-4V (Grade 5).
 Titanium Grade 18 (UNS R56322) is identical to Grade 9 in all respects with the exception of the additional 0.04 – 0.08% palladium to increase corrosion resistance.
 Titanium Grades 9 and 18 have a density of 4.48 g/cc - less than 60% that of steel.

CORROSION RESISTANCE

This material offers good corrosion resistance in oxidising, neutral and mildly reducing media, including chlorides.
 Titanium Grade 18 with the addition of palladium offers greater resistance to corrosion.
 The alloy resists oxidation up to 600°F (316°C).

MATERIAL SPECIFICATIONS

Aerospace

- WNr. 3.7194
- AIR9182 TA32.5V
- AMS 4943
- AMS 4944
- AMS 4945
- AMS 4989

Commercial

- WNr. 3.7195
- UNS R56320
- ASTM B348
- ASTM B265
- ASTM B338
- ASTM B863
- ASTM B381
- ASTM B861

FABRICATION

Weldability – good
 Specific bend radius <0.070 x thickness – 2.5 (typical)

AVAILABILITY

Bar, wire, strip, sheet, plate, foil, forgings, seamless and welded pipe/tube (for Titanium Grades 9 and 18)

CHEMICAL COMPOSITION

Weight %	C	Fe	N ₂	O ₂	H ₂	Al	V
Min.						2.5	2.0
Max.	0.08	0.25	0.03	0.15	0.015	3.5	3.0

MECHANICAL PROPERTIES

	Minimum	Typical
UTS, MPa	621	740
0.2% PS, MPa	483	607
Elongation on 2 in., %	15	17
Charpy V notch impact, J (L direction pipe)	48	-
Elastic modulus, GPa	-	91
Hardness, HRC	-	15

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007