

ALUMINIUM DRAWN/ROLLED/COLD FINISHED, BAR, ROD, WIRE SHAPES

TYPICAL APPLICATIONS

Aerospace Components
 Defence Components
 High Technology Applications

PRODUCT DESCRIPTION

A high strength 5.1 to 6.1% Zinc alloy. Solution treated, artificially aged and controlled stretched to achieve the T651 condition, in drawn, rolled, cold finished wire, bar and profile form.

General Engineering Euronorm - EN 573 / 754
 AECMA Euronorm - No Current Norm

STOCK RANGE

- Round Bar** : 1/2" to 7" Diameter (12.7 To 177.8mm)
- Flat** : 2" X 1/4" to 6" X 4" (50.8 X 6.35 to 152.4 X 101.6mm)
- Squares** : 3/4" to 6" Square (19.05 to 152.4mm)

CUT TO SIZE SAWN BLANKS

Cut to Length + 1.0mm - NIL

MACHINABILITY

Very Good

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Fair

SURFACE TREATMENT

Anodising

- Protective - Fair
- Bright - Variable
- Hard - Fair
- Colour - Fair

Plating

N/A

Vitreous Enamelling

N/A

WELDABILITY

- Brazing & Soldering - Not Recommended
- Oxygen - Not Recommended
- Inert Gas - Not Recommended
- Resistance, Spot, Beam - Very Good

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Tables 10.12 to 10.20 of U.S. Aluminium Standards & Data. For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min	REM			1.20		2.10	0.18	5.10		0.05 Each (Max)
Max	REM	0.40	0.50	2.00	0.30	2.90	0.28	6.10	0.20	0.15 Total

MECHANICAL PROPERTIES (MINIMA)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65 √ S ₀ (%)	Elongation on 50mm (%)
Up to 4.000	77	66	-	7
4.001 – 6.000	75	64	-	7
6.001 – 7.000	73	62	-	7

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007