

ALUMINIUM ALCLAD SHEET

TYPICAL APPLICATIONS

Aerospace Components
 Defence Components
 High Technology Applications

PRODUCT DESCRIPTION

A high strength 5.1 to 6.1% Zinc alloy solution heat treated and artificially aged to achieve the T6 condition. Also generally available in the 'O' condition for more severe, bending and forming operations.

AECMA Euronorm - BS EN 2092 (T6)

STOCK RANGE

0.008" to 0.249" Thick
 (0.203 to 6.32mm)

CUT TO SIZE GUILLOTINED BLANKS

Edge deviation over cut length/width +/- 0.2mm per m (maximum thickness 6.35mm)

FORMABILITY

Fair for 'O' condition.

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Very Good

SURFACE TREATMENT

Anodising

- Protective - Excellent
- Bright - Very Good
- Hard - Excellent
- Colour - Very Good

Plating

Special pre-treatment necessary to achieve successful results

Vitreous Enamelling

As Plating.

WELDABILITY

Please contact our Technical Department.

PRODUCTION TOLERANCES

Manufacturing limits are as stated in Table 7.7b to 7.18 in U.S. Aluminium Standards and Data. For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min	REM			1.2		2.10	0.18	5.10		0.05 Each (Max)
Max	REM	0.40	0.50	2.0	0.30	2.90	0.28	6.10	0.20	0.15 Total

MECHANICAL PROPERTIES (MINIMA)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65 √ S ₀ (%)	Elongation on 50mm (%)
0.008 – 0.011	68	58	5	-
0.012 – 0.039	71	61	8	-
0.040 – 0.062	72	62	9	-
0.063 – 0.125	74	64	9	-
0.126 – 0.187	74	64	9	-
0.188 – 0.249	76	65	9	-

NB: Figures shown above are for 'T6' condition.

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007