

TITANIUM

TYPICAL APPLICATIONS

Components/equipment for architecture, medical engineering, automotive, chemical plant, pharmaceutical, brewing, food, oil & gas, pulp & paper and marine industries.

PRODUCT DESCRIPTION

CP (Commercially Pure) Grade 3 is unalloyed titanium providing higher mechanical strength (typical yield strength 462 MPa) compared with CP Grades 1 and 2 and ASME code case allowable stresses combined with moderate ductility and excellent weldability. Grade 3 titanium has a density of 4.51 g/cc - less than 60% that of steel.

CORROSION RESISTANCE

This material offers high corrosion resistance in oxidising, neutral and mildly reducing media, including chlorides.

MATERIAL SPECIFICATIONS

- UNS R50550
- ASTM B348 Grade 3
- W. Nr. 3.7055
- AMS 4900
- AIR 9182 T-50
- ASTM 265 Grade 3

FABRICATION

Weldability – excellent
 Specified bend radius for <0.070 in. x thickness – 2.0
 Specified bend radius for >0.070 in. x thickness – 2.5
 Welded bend radius x thickness – 3.0 (min.)

AVAILABILITY

Bar, wire, strip, sheet, plate, seamless and welded pipe.

CHEMICAL COMPOSITION

Weight %	C	Fe	N ₂	O ₂	H ₂ (sheet)	H(bar)	Ti
Min.							
Max.	0.1	0.3	0.05	0.35	0.015	0.0125	Balance

MECHANICAL PROPERTIES

	Minimum	Typical
UTS, MPa	448	593
0.2% PS, MPa	379	462
Elongation on 2 in., %	18	25
Reduction of area, %	35	-
Elastic modulus, GPa	-	103
Charpy, V notch impact, J	20	-
Hardness, HBN	-	200

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007