

## ALUMINIUM ALCLAD SHEET

### TYPICAL APPLICATIONS

Aerospace Components  
 Defence Components  
 High Technology Applications

### PRODUCT DESCRIPTION

A high strength 3.9 to 5% Copper alloy rolled sheet, clad with 1050A, solution heat treated, cold worked and naturally aged to a substantially stable condition, to achieve T3 condition.

General Engineering Old BS - HC15TB (BS 1470)  
 AECMA Euronorm - None

### STOCK RANGE

0.0118" to 0.236" Thick  
 (0.3 to 6mm)

### CUT TO SIZE GUILLOTINED BLANKS

Edge deviation over cut length/width  $\pm 0.2$ mm per m (maximum thickness 6.35mm)

### FORMABILITY

Good.

### CORROSION RESISTANCE

#### Resistance to Atmospheric Attack

Very Good.

### SURFACE TREATMENT

#### Anodising

- Protective - Excellent
- Bright - Very Good
- Hard - Excellent
- Colour - Excellent

#### Plating

Very Good

#### Vitreous Enamelling

Good

### WELDABILITY

Please contact our Technical Department.

### PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Section 9 of BS 4L100 – Tables 15 (F2, 4, 5, 6 & 7). For further assistance please contact our Sales Dept / Laboratory.

### CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti + Zr	Ti	Others
Min	Rem	0.50		3.9	0.40	0.20						0.05 Each (Max)
Max	Rem	0.90	0.50	5.0	1.20	0.80	0.10	0.10	0.25	0.20	0.15	0.15 (Total)

### MECHANICAL PROPERTIES (MINIMA)

Size Range (mm)		Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on $5.65 \sqrt{S_0}$ (%)	Elongation on 50mm (%)
Over	Up to & Including				
0.4	0.8	385	245	-	13
0.8	1.6	385	245	-	14
1.6	6.0	390	250	-	14

### TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

### Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007