

ENGINEERING RAW MATERIALS

TYPICAL APPLICATIONS

Aero-engine components, Airframe components, Marine equipment, Offshore oil & gas equipment, Power generation industry, Autosport components, Medical equipment.

PRODUCT DESCRIPTION

Ti-6Al-4V (Grade 5), classed as an alpha-beta alloy, is the most widely used of the high strength titanium alloys. The alloy combines its good mechanical strength and low density (4.42 kg/dm³) with excellent corrosion resistance in many media. Grade 5 titanium is fully heat treatable (solution heat treatment plus aging) in sections up to 25mm and can be employed up to around 400°C.

Ti-6Al-4V ELI (Grade 23) has a reduced oxygen content (0.13% max.) compared with Grade 5. This confers improved ductility and fracture toughness with some reduction in mechanical strength. Uses include fracture critical airframe structures and for offshore tubulars.

CORROSION RESISTANCE

Grade 5 titanium offers excellent resistance to many marine and offshore oil & gas environments. Titanium and its alloys resist a wide range of acid conditions being highly resistant to oxidising acids, possessing useful resistance to reducing acids and offering good resistance to most organic acids at lower concentrations and temperatures. Titanium should not be used with red fuming nitric acid and is rapidly attacked by hydrofluoric acid. The addition of 0.05% palladium (grade 24), 0.1% ruthenium (grade 29) and 0.05% palladium and 0.5% nickel (grade 25) significantly increases corrosion resistance in reducing acid chloride and sour environments, raising the threshold temperature to well over 200°C.

MECHANICAL PROPERTIES (Bar to ASTM B348 Grade 5)

	Minimum	Typical
UTS, MPa	895	1,000
0.2% PS, MPa	828	910
Elongation, % in 4D	10	18
Reduction of area, %	25	-
Elastic modulus, GPa	-	114
Hardness, HRC	-	36
Charpy V-notch impact, J	-	24

MATERIAL SPECIFICATIONS

- UNS R56400
- ASTM B348 Grade 5
- BS 2TA11
- AMS 4911
- AMS 4928
- MIL-STD-2154

FABRICATION

Weldability – fair

Specified bend radius for <0.070 in. x thickness - 4.5

Specified bend radius for >0.070 in. x thickness - 5.0

(typical values)

AVAILABILITY

Bar, wire, sheet, plate, extrusions, forgings, seamless pipe/tube.

CHEMICAL COMPOSITION

(Bar to ASTM B348 Grade 5)

%	N	C	H	Fe	O	Al	V
Min.						5.5	3.5
Max.	0.05	0.08	0.015	0.40	0.20	6.75	4.5

Smiths High Performance
Unit O
Stratton Business Park
London Road
Biggleswade
Beds
SG18 8QB

Tel: 01767 604 708
Fax: 01767 312 885
Email: info@smithshp.com

For more information about our company and the rest of our product range please visit our website at:
www.SmithsHP.com