

## DUPLEX STAINLESS STEEL

### TYPICAL APPLICATIONS

Pumps, valves, chokes, Xmas trees, pipework / flanges, bolting, connectors & manifolds. In oil and gas industry. Equipment in brewing, power generation and chemical engineering.

### PRODUCT DESCRIPTION

Material to UNS S31803 (and the other specifications listed below) is described as a duplex stainless steel with a microstructure of 50:50 austenite and ferrite. The steel combines good mechanical strength (typically up to over 480 MPa yield strength) and ductility with moderate to good corrosion resistance in a variety of environments. By agreement, the alloy can be supplied with a PReN (Pitting Resistance Equivalent) at >34 which ensures that the resistance to pitting corrosion is as high as possible for this alloy grade. In addition, the steel offers good resistance to stress corrosion cracking. Ambient and subzero temperature notch ductility is good. These attributes mean that this duplex steel can be used successfully as an alternative to 300 series stainless steels in applications where higher

mechanical strength / lower weight is required and / or resistance to stress corrosion cracking is needed.

### AVAILABILITY

Bar, forgings, sheet, plate, pipe, tube, closed die forgings, flanges and welding consumables.

### MATERIAL SPECIFICATIONS

- UNS S31803 in various ASTM product form specifications
- EN 10088-3 1.4462 (Grade X2CrNiMoN22-5-3)
- NORSOK MDS D41 to D45, D47 & D48
- ASTM A182 F51
- NACE MR01-75 (latest revision) / ISO 15156

### MACHINABILITY / WELDING

The machining and welding of this grade of duplex stainless steel presents no particular problems. Guidance notes are available upon request.

### CHEMICAL COMPOSITION % (EN 10088-3 1.4462)

Weight (%)	C	Mn	Si	S	P	Cr	Ni	Mo	N	PReN
Min.						21.0	4.5	2.5	0.10	33 - 34 Typical
Max	0.03	2.00	1.00	0.015	0.035	23.0	6.5	3.5	0.22	

PReN = Cr % + 3.3Mo% + 16N%

### MINIMUM MECHANICAL PROPERTIES AT ROOM TEMPERATURE (EN 10088-3 1.4462 MAX DIAMETER 160mm – SOLUTION TREATED)

Ultimate Tensile Strength	650 – 880 MPa	( 94 – 128 ksi )
0.2% Proof Strength	450 MPa	( 65 ksi )
Elongation	25 %	
Hardness (Max)	270 HB	
Impact	100 J	( 74 ft.lb )

### TYPICAL PHYSICAL PROPERTIES

Density	7.8	kg/dm <sup>3</sup>
Specific Thermal Capacity at 20 <sup>0</sup> C	500	J.Kg <sup>-1</sup> .K <sup>-1</sup>
Mean Coefficient of Thermal Expansion at 20 - 100 <sup>0</sup> C	13.0	x 10 <sup>-6</sup> K <sup>-1</sup>
Thermal Conductivity at 20 <sup>0</sup> C	15	W.m <sup>-1</sup> .K <sup>-1</sup>
Electrical Resistivity at 20 <sup>0</sup> C	0.80	Ω .mm <sup>2</sup> .m <sup>-1</sup>
Modulus of Elasticity at 20 <sup>0</sup> C	200	GPa
Magnetisable	Yes	

### TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

### Smiths High Performance

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 708

Fax: +44 (0) 01767 312 885

Email: sales@smithshp.com

Website: www.smithshp.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007