

2055-T84 Aluminium

Smiths High Performance



Revision: SHP/english/datasheets/2055-t84-extrusions/11.02.2025

Page: 1 of 2

High Strength, Fatigue Resistant, Low-Density Extrusions

For motorsport & aerospace applications

We have developed Al-Li alloy 2055 extrusions for use in motorsport, aerospace and other applications requiring high tensile or compressive strength, high modulus, high fatigue resistance and low density with good fracture toughness and corrosion resistance.

Li additions increase the strength and modulus of Al-Li alloys while lowering their density. The density of 2055 is 4 to 5% less than high-strength 7xxx alloys. 2055-T84 extrusions exhibit superior machining, finishing and forming characteristics.

Applications:

The combination of high strength, stiffness, damage tolerance and durability makes 2055 suitable as a replacement for high-strength 7xxx and 2xxx alloys in applications such as fuselage stringers, floor beams, compressor wheels, turbo impellers and other statically and dynamically loaded applications requiring high strength and stiffness.

Commercial Status:

Alloy 2055-T84 extrusions are covered by AMS 4257.


Material design allowables, including static properties, physical properties, fracture toughness, corrosion resistance and S-N fatigue, are available in MMPDS.

Toughness & Fatigue:

The damage tolerance and durability properties of 2055-T84 extrusions are superior to high-strength 7xxx extrusions providing an improved combination of strength and toughness improved fatigue crack growth resistance and S-N fatigue resistance.

About Smiths High Performance

Smiths High Performance is a leading stockholder and supplier of high-performance engineering materials. We are material supply chain partners supporting high-technology market sectors.



Chemical Composition

Chemical Composition Limits • AA 2055 (Wt.%)^{*}

	Cu	Li	Zn	Ag	Mg
Min:	3.20	1.00	0.30	0.20	0.20
Max:	4.20	1.30	0.70	0.70	0.60
	Mn	Zr	Fe	Si	Al
Min:	0.10	0.05			
Max:	0.50	0.15	0.10	0.07	Rem

^{*} Other elements: 0.05 wt.% max (each);
0.15 wt.% max (total); Ti 0.10 max



Further technical data available on the reverse of this Datasheet

2055-T84 Aluminium

Smiths High Performance



Revision: SHP/english/datasheets/2055-t84-extrusions/11.02.2025

Page: 2 of 2

Mechanical Properties:

The strength of 2055-T84 extrusions is considerably higher compared to 7150 extrusions and superior to that of older 7xxx alloys such as 7075 and 7050 while providing higher stiffness, comparable or better fracture toughness and lower density.

Corrosion Resistance:

The exfoliation corrosion and stress corrosion cracking resistance of 2055-T84 extrusions is similar to or better than that of 7xxx alloys in the T76 and T77 tempers and superior to the T6 tempers. The typical exfoliation rating is P (pitting, no exfoliation). The minimum guaranteed SCC resistance (ASTM G47) in the ST direction is 25 ksi (172 MPa).

Other characteristics include superior corrosion resistance in accelerated and seacoast environments.

Static Properties for 2055-T84 Extrusions - MMPDS Minimum Values (A- or S-Basis)

Property	Dir	2055-T84 Extrusions (AMS 4257)					
	Thickness:						
	(in.)	0.040 - 0.125	0.126 - 0.249	0.250 - 0.499	0.500 - 0.749	0.750 - 1.249	1.250 - 1.500
	mm	1.02 - 3.18	3.20 - 6.32	6.35 - 12.67	12.70 - 19.02	19.05 - 31.72	31.75 - 38.10
Ult. Tensile, F_{tu} (A), ksi (MPa)	L	82 (565)	83 (572)	85 (586)	87 (600)	88 (607)	90(620)
	LT	---	84 (579)	84 (579)	84 (579)	84 (579)	84(579)
Yield Strength, F_{ty} (A), ksi (MPa)	L	78 (538)	79 (545)	80 (552)	82 (565)	84 (579)	86(593)
	LT	---	78 (538)	78 (538)	78 (538)	78 (538)	78(538)
% Elongation (S) (4D)	L	5	6	7	8	8	8
	LT	---	5	5	5	5	5
Comp. Yield Strength, F_{cy} (A), ksi (MPa)	L	80 (552)	81 (558)	81 (558)	83 (572)	84(579)	87(600)
	LT	---	---	---	---	---	---
Fracture Toughness, K_{Ic} , ksi/in (MPa√m)	L	---	---	---	---	22(24)	22(24)
	LT	---	---	---	---	19(21)	19(21)

...where performance matters...

When you purchase high-performance materials from **Smiths High Performance**, you will join some of the biggest and best global engineering companies. We are a Tier 1 supply chain partner to the world's leading motorsport companies. Our unique business structure and ethos allow us to offer services otherwise unavailable in this market sector.

www.smithshp.com

info@smithshp.com



Unit 3, Juno Place
Stratton Business Park
Biggleswade SG18 8XP

Tel: +44 (0)1767 604 708



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.