

AZ31B Magnesium

Smiths High Performance



Revision: SHP/english/datasheets/az31b/11.02.2025

Page: 1 of 1

Rapid Machining

A wrought magnesium alloy offering good room temperature strength.

Available in round bar, flat bar, forgings and plate, AZ31B magnesium alloy benefits from increased strength and density due to strain hardening with partial anneal (H24 and H26 tempers).

The alloy offers excellent weldability and can be machined faster than any other metal. The material is non-magnetic with high electrical and thermal conductivity.

Chemical Composition (weight %)

	Mg	Al	Zn	Mn	
Min.	Bal	2.50	0.70	0.20	
Max.	Bal	3.50	1.30	1.00	



Mechanical Properties (minimum tensile properties)

AZ31B-O 0.5 - 1.5mm		AZ31B-O 1.5 - 6.3mm		AZ31B-O 6.3 - 75mm		AZ31B-H24 0.5 - 6.3mm	
0.2% Proof Stress	125 MPa	0.2% Proof Stress	105 MPa	0.2% Proof Stress	105 MPa	0.2% Proof Stress	200 MPa
Tensile Strength	220 MPa	Tensile Strength	220 MPa	Tensile Strength	220 MPa	Tensile Strength	270 MPa
Elongation in 5.65vA	10%	Elongation in 5.65vA	10%	Elongation in 5.65vA	8%	Elongation in 5.65vA	5%

Characteristics:

- Good ductility and corrosion resistance
- High electrical and thermal conductivity
- Good strength at room temperature

Applications:

- Production of intricate motorsport parts
- Monocoque construction
- Race chassis, structural engine parts, hydraulics

About Smiths High Performance

Smiths High Performance is a leading stockholder and supplier of high-performance engineering materials. We are material supply chain partners supporting high-technology market sectors.


www.smithshp.com
info@smithshp.com


Unit 3, Juno Place
Stratton Business Park
Biggleswade SG18 8XP

Tel: +44 (0)1767 604 708



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.