15CDV6 - Heat-Treatable Steel

Product Datasheet

Revision: SHP/15CDV6/11/2017



...where performance matters

Chromium-Vanadium Alloy

15CDV6 is a chromium, molybdenum, vanadium heat-treatable steel with high strength after heat treatment (1080-1280 N/mm²).

The alloy is easily welded and does not require localised heat treatment after welding. 15CDV6 combines outstanding yield strength with good toughness. In motorsport applications, the product offers a cost-effective solution in areas where a combination of high strength and excellent weldability is required.



Chemical Composition

Weight (%)	С	N	0	Fe	Al	Sn	Zn	Мо	Si	н
Min. Max.	0.08	0.05	0.12	0.25	5.5 6.5	1.75 2.25	4.5	2.25	0.10	0.0125

Mechanical Properties

Condition	0.2% Proof Stress	Tensile Strength	Elongation	Hardness
1.7734.2 (Annealed)	-	-	-	197 HB
1.7734.4	550 MPA Min.	700 MPA Min.	13 % Min.	-
1.7734.5	790 MPA Min.	980-1180 MPA Min.	11 % Min.	-
1.7734.6	930 MPA Min.	1080-1250 MPA Min.	10 % Min.	-

Characteristics

- Chromium Vanadium Steel
- Easily welded
- Outstanding yield strength
- Good toughness
- Heat treatable

Applications

- Motorsport Applications
- Suspension components
- Track and pushrods
- Roll cages
- Uprights and wishbones

About Smiths High Performance

Smiths High Performance is a leading stockholder and supplier of high-performance engineering materials to the global motorsport sector. We are supply partners in a range of specialist motorsport markets including **Formula 1, Formula E, NASCAR, MOTO GP, WEC & WRC**.

www.**smithshp**.com



Unit 3, Juno Place Stratton Business Park Biggleswade SG18 8XP

Tel: +44 (0)1767 604 708





info@smithshp.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.