SHP 6246 Ultimate

Product Data Sheet

Revision: SHP/6246/10/2016



...where performance matters

Titanium Alloy

6246 Titanium Alloy (a stronger derivative of 6-2-4-2) is an alpha-beta titanium alloy offering very high mechanical strength with good retention up to 460 °C.

The alloy is heat treatable and deep hardenable. Corrosion resistance is good and the material is approved for sour service in the NACE MR-01-75 standard.

The alloy is heat treatable and deep hardenable. The corrosion resistance of the material is good. 6246 titanium is ideal in sour service environments and is NACE MR

Material applications include production equipment in the oil and gas sector, gas turbine engine components in the aerospace sector and production of precision components for motorsport.





Typical Applications:

- · Racing engine parts
- Racing engine drivetrain components
- Gas turbine components
- Compressor discs and fan blades
- Suitable for sour service applications

Stock Availability:

Round bar





About Smiths High Performance

Smiths High Performance is a leading stockholder and supplier of high-performance engineering materials to the global motorsport sector. We are supply partners in a range of specialist motorsport markets including Formula 1, Formula E, NASCAR, MOTO GP, WEC & WRC.

Further technical data available on the reverse of this Datasheet

www.smithshp.com info@smithshp.com

Revision: SHP/6246/10/2016

...where performance matters

Chemical Composition

Weight (%)	Al	Zr	Sn	Мо	Fe	0	С	N	Н	Υ	Each	Total
Min. Max.	5.5 6.5	3.5 4.5	1.75 2.25		0.15	0.15	0.04	0.04	0.0125	0.005	0.10	0.40

Minimum Mechanical Properties for AMS 4981

Alloy	Round Bar	Longitudin	al Direction	Elong.	Traverse	Elong.	
	Dia (mm)	Rm in MPa	Rp 0.2 Mpa	A4 in %	Rm in MPa	Rp 0.2 MPa	A4 in %
6246	12.7 - 63.5	1172	1103	10	1172	1103	8
6246	63.5 - 76.2				1138	1069	6
6246	76.2 - 101.6				1103	1034	6

Minimum Guaranteed Mechanical Properties for SHP 6246 Ultimate

Alloy	Round Bar Dia (mm)	Longitudin Rm in MPa	al Direction Rp 0.2 Mpa	Elong. A4 in %	Traverse Rm in MPa		Elong. A4 in %
6246 6246	< 50.8 * > 50.8 - 200 **	1350	1300	5	1300	1250	3

- Supplied in the solution treated & aged condition
- ** 25mm thick sample capability test / supplied in the annealed condition

...where performance matters...

When you purchase high-performance materials from Smiths High Performance, you will be joining some of the biggest and best global engineering companies. We are a Tier 1 supply chain partner to the world's leading motorsport companies. Our unique business structure and ethos allows us to offer services which are otherwise unavailable in this market sector.

www.smithshp.com info@smithshp.com



Unit 3, Juno Place Stratton Business Park Biggleswade SG18 8XP

Tel: +44 (0)1767 604 708



