

C300 Maraging Steel

Product Datasheet




Revision: SHP/C300/09/2018

...where performance matters

For strength and malleability

C300 Maraging Steel offers stable properties and weight reduction possibilities while still maintaining strength

C300 maraging steel is age hardenable steel produced to create exceptional toughness and strength. With a nominal tensile strength of 300 ksi, the material can retain its tensile strength up to 450°C. The core alloying elements are iron, cobalt, nickel and molybdenum, and the product offers excellent toughness and resistance to crack propagation. The material may also be nitrided. C300 can be machined close to finished dimensions as the low-temperature maraging treatment results in minimal distortion.



Characteristics

- Excellent strength and toughness
- Excellent resistance to crack propagation
- Can be readily welded
- Retains properties with no loss of malleability

Applications

- Torsion bars
- Chassis components
- Crankshafts
- Gears

Chemical Composition (weight = %)

	C	Si	Mn	Ni	Co	Mo	Al	Ti	Fe
Min				18.00	8.50	4.60	0.05	0.50	Bal
Max	0.3	0.10	0.10	19.00	9.50	5.20	0.15	0.80	Bal

Mechanical Properties (annealed and maraged condition)

UTS, MPa	0.2%PS, MPa	Elongation on 4D, %	Charpy Notch Impact, J	Youngs Modulus GPa
2,035	2,000	12	17	195

Hardness (HRC) in the annealed condition is 36 max. and for the maraged condition 52 min.

About Smiths High Performance

Smiths High Performance is a leading stockholder and supplier of high-performance engineering materials to the global motorsport sector. We are supply partners in a range of specialist motorsport markets including Formula 1, Formula E, NASCAR, MOTO GP, WEC & WRC.

www.smithshp.com

info@smithshp.com



Unit 3, Juno Place
Stratton Business Park
Biggleswade SG18 8XP
Tel: +44 (0)1767 604 708



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.